



SAKATA 3D Flex-920 is a biodegradable and partially renewable flexible filament, developed specifically for FDM/FFF 3D printers. It shows a Shore A hardness of 89, high thermal and chemical resistances, very good adhesion to the bed and an excellent impact resistance. Despite being a flexible material, it can be printed very easily. Ideal for parts that require high impact resistance and/or flexibility, such as tires, belt, etc. Manufactured in Spain by POLIMERSIA GLOBAL S.L.

FILAMENT SPECIFICATIONS	Unit	Value
Diameter	mm	1.75 ± 0.03
Max. roundness deviation	mm	0.03
Net weight	g	1,000

PHYSICAL PROPERTIES	Standard	Unit	Value
Density	ISO 1183	g/cm ³	1.23 – 1.27
Hardness	ISO 868	Shore A	89
MECHANICAL PROPERTIES	Standard	Unit	Value
Tensile modulus ⁽¹⁾	ISO 527	MPa	NA
Tensile strength at break ⁽¹⁾	ISO 527	MPa	NA
Elongation at break ⁽¹⁾	ISO 527	%	NA
Flexural modulus ⁽¹⁾	ISO 178	MPa	NA
Flexural strength ⁽¹⁾	ISO 178	MPa	NA
Charpy notched impact strength ⁽¹⁾	ISO 179	KJ/m ²	NA
Charpy unnotched impact strength ⁽¹⁾	ISO 179	KJ/m ²	NA
THERMAL PROPERTIES	Standard	Unit	Value
VICAT ⁽¹⁾	ISO 306	°C	84
HDT (0,45 MPa) ⁽¹⁾	ISO 75-1, 75-2	°C	61

NA = not available.

⁽¹⁾ 3D printing bars, 4mm thickness.

PRINT SETTINGS ^(*)	Unit	Value
Nozzle temp.	°C	220 - 245
Type of nozzle	-	Brass
Bed temp.	°C	< 40
Type of bed	-	Glass or PEI
Bed treatment	-	Not needed
Closure chamber	-	Not needed
Cooling fan	%	100
Layer height	mm	0.2
Print speed	mm/s	10 - 50
Dry specification	Before printing	2 – 4 hours at 60 °C (optional)
	During printing	60 °C (optional)

^(*) Settings are based on a 0.4 mm nozzle.

Certifications / Approvals

SAKATA 3D PLA Flex-920 filament is not certified for food contact either medical applications.

Safety Considerations

Good general ventilation of the workplace is recommended.

**Disclaimer**

The above information is provided in good faith. POLIMERSIA GLOBAL S.L. makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties, representations and conditions, including without limitation all warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose.