



SAKATA 3D PET-G VO filament is a 3D printing compound based on Glycol modified Polyethylene Terephthalate (PET-G) with a flammability V-0 according to UL 94. This material is free of halogens-based flame retardants and red phosphorous and does not contain any per- and polyfluoroalkyl substances (PFAS-free product). It shows similar properties than standard PET-G: easy to print, low shrinkage, high-temperature resistance, dimensional stability, good layer adhesion and mechanical properties. Ideal for applications where fire resistance is important, electronic components, prototyping. Made in Spain by POLIMERSIA GLOBAL S.L.

FILAMENT SPECIFICATIONS	Unit	Value
Diameter	mm	1.75 ± 0.03
Max. roundness deviation	mm	0.03
Net weight	g	1.000

PHYSICAL PROPERTIES	Standard	Unit	Value
Density	ISO 1183	g/cm ³	1.26
MECHANICAL PROPERTIES	Standard	Unit	Value
Tensile modulus ⁽¹⁾	ISO 527	MPa	2,350
Tensile strength (at yield) ⁽¹⁾	ISO 527	MPa	40
Elongation at break ⁽¹⁾	ISO 527	%	40
Charpy unnotched impact strength ⁽¹⁾	ISO 179	KJ/m ²	NB
Charpy notched impact strength ⁽¹⁾	ISO 179	KJ/m ²	3
THERMAL PROPERTIES	Standard	Unit	Value
HDT (0.45 MPa) ⁽¹⁾	ISO 75	°C	63
HDT (1.8 MPa) ⁽¹⁾	ISO 75	°C	58
VICAT ⁽¹⁾	ISO 306	°C	70
FLAMMABILITY	Standard	Unit	Value
Oxygen Index ⁽¹⁾	ASTM D 2863	%	35
Flammability rating 1.5 mm thickness ⁽²⁾	UL 94	rating	V-0
Flammability rating 3.0 mm thickness ⁽²⁾	UL 94	rating	V-0
Glow Wire Flammability Index ⁽¹⁾	IEC 60695-2-12		960@1mm
Glow Wire Flammability Index ⁽¹⁾	IEC 60695-2-12		960@2mm
Glow Wire Ignition Test ⁽¹⁾	IEC 60695-2-13		775@1mm
Glow Wire Ignition Test ⁽¹⁾	IEC 60695-2-13		775@2mm
ELECTRICAL PROPERTIES	Standard	Unit	Value
Comparative Tracking Index – solution A ⁽¹⁾	IEC 60114	V	600

NB: No break.

⁽¹⁾ Injection moulding bars.

⁽²⁾ 3D Printed flame bars 125(±5) x 13.0(±0.5) mm.

PRINT SETTINGS	Unit	Value
Nozzle temp.	°C	235 - 250
Type of nozzle	-	Brass
Bed temp.	°C	> 70
Type of bed	-	Glass or PEI
Fan speed	%	40 - 90
Layer height	mm	0.2
Print speed	mm/s	20 - 250
Dry specification	Before printing	4 – 6 hours at 60 °C
	During printing	60 °C (optional)

**Certifications / Approvals**

The filament is not certified for food contact either medical applications.
The filament is not certified by Underwriters Laboratories and has no UL number.

Safety Considerations

Good general ventilation of the workplace is recommended.

Disclaimer

The above information is provided in good faith. POLIMERSIA GLOBAL S.L. makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties, representations and conditions, including without limitation all warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose.