

SAKATA 3D PLA HS (High Speed) is a biodegradable high-speed filament specifically developed for printing speeds of up to 500 mm/s without compromising quality. This material ensures an excellent smooth printing, adhesion to bed, layer bonding, efficiency and precision, and minimal warping. Ideal for quick prototyping and high-volume production. Made in Spain by POLIMERSIA GLOBAL S.L.

FILAMENT SPECIFICATIONS	Unit	Value
Diameter	mm	1.75 ± 0.03
Max. roundness deviation	mm	0.03
Net weight	g	1,000

PHYSICAL PROPERTIES	Standard	Unit	Value
Density	ISO 1183	g/cm ³	1.32
MECHANICAL PROPERTIES	Standard	Unit	Value
Tensile modulus ⁽¹⁾	ISO 527	MPa	NA
Tensile strength at break ⁽¹⁾	ISO 527	MPa	42
Elongation at break ⁽¹⁾	ISO 527	%	6
Flexural modulus ⁽¹⁾	ISO 178	MPa	NA
Flexural strength ⁽¹⁾	ISO 178	MPa	NA
Charpy notched impact strength ⁽¹⁾	ISO 179	KJ/m ²	NA
Charpy unnotched impact strength ⁽¹⁾	ISO 179	KJ/m ²	NA
THERMAL PROPERTIES	Standard	Unit	Value
HDT (0.45 MPa) ⁽¹⁾	ISO 75-1/2	°C	60
Vicat ⁽¹⁾	UNE-EN-ISO 306	°C	60

⁽¹⁾ 3D printing bars.

PRINT SETTINGS ^(*)	Unit	Value
Nozzle temp.	°C	Classic: 190 - 210 High speed: 210 - 230
Type of nozzle	-	Brass
Bed temp.	°C	> 45
Type of bed	-	Glass or PEI
Bed treatment	-	Adhesive spray or stick when needed
Closure chamber	-	Not needed
Cooling fan	%	100
Layer height	mm	0.1 – 0.3
Print speed	mm/s	Classic :50 - 100 High-speed: 100 - 500
Max. volumetric speed	mm ³ /s	34
Dry specification	Before printing	4 – 6 hours at 55 °C (optional)
	During printing	55 °C (optional)

^(*) Settings are based on a 0.4 mm nozzle.

Certifications / Approvals

SAKATA 3D PLA HS filament is not certified for food contact either medical applications.

Safety Considerations

Good general ventilation of the workplace is recommended.

Disclaimer

The above information is provided in good faith. POLIMERSIA GLOBAL S.L. makes no warranty or representation of any kind, regarding the information given or the products described, and expressly disclaims all implied warranties, representations and conditions, including without limitation all warranties and conditions of quality, merchantability and suitability or fitness for a particular purpose.